Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-19-11** **Date: 24/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-11 /01

Customer ID : M30 Concrete, Pavement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete, Pavement Concrete	M30	17/04/2018	24/04/2018	150.64 X 149.24 X 149.74	22481	8.172	577.5	25.7	25.5
2	M30 Concrete, Pavement Concrete	M30	17/04/2018	24/04/2018	151.02 X 149.89 X 151.11	22636	8.386	605.2	26.7	
3	M30 Concrete, Pavement Concrete	M30	17/04/2018	24/04/2018	150.77 X 150.93 X 150.43	22757	8.384	547.8	24.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

AE & WO

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-19-11** **Date: 15/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-11 /02

Customer ID : M30 Concrete, Pavement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete, Pavement Concrete	M30	17/04/2018	15/05/2018	150.22 X 150.54 X 150.55	22614	8.111	407.1	18.0	18.4
2	M30 Concrete, Pavement Concrete	M30	17/04/2018	15/05/2018	150.22 X 150.54 X 150.55	22614	8.111	411.6	18.2	
3	M30 Concrete, Pavement Concrete	M30	17/04/2018	15/05/2018	150.22 X 150.54 X 150.55	22614	8.111	429.7	19.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-23-06** **Date: 27/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-04-18

Sample ID No : 2018-04-23-06 /01

Customer ID : M30 Concrete, Pavement Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete, Pavement Concrete	M30	20/04/2018	27/04/2018	149.40 X 151.89 X 150.56	22692	8.027	587.0	25.9	25.5
2	M30 Concrete, Pavement Concrete	M30	20/04/2018	27/04/2018	149.33 X 151.48 X 149.58	22621	8.118	595.8	26.3	
3	M30 Concrete, Pavement Concrete	M30	20/04/2018	27/04/2018	150.88 X 149.26 X 150.94	22520	8.383	550.3	24.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-04-23-06** **Date: 18/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-04-18
Sample ID No	:	2018-04-23-06 /02
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	20/04/2018	18/05/2018	151.42 X 151.92 X 149.36	23005	8.536	770.0	33.5	33.2
2	M30 Concrete	M30	20/04/2018	18/05/2018	151.88 X 151.29 X 149.22	22977	8.199	753.5	32.8	
3	M30 Concrete	M30	20/04/2018	18/05/2018	150.86 X 149.01 X 150.22	22479	8.471	750.5	33.4	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-05-03** **Date: 10/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-05-18
Sample ID No	:	2018-05-05-03 /01
Customer ID	:	M30 Concrete, Pavement Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	10/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross seetional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete, Pavement Concrete	M30	03/05/2018	10/05/2018	151.37 X 149.39 X 149.45	22613	8.353	573.7	25.4	25.4
2	M30 Concrete, Pavement Concrete	M30	03/05/2018	10/05/2018	149.24 X 150.29 X 149.94	22429	8.442	590.2	26.3	
3	M30 Concrete, Pavement Concrete	M30	03/05/2018	10/05/2018	150.75 X 150.19 X 149.83	22640	8.177	556.7	24.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-05-03** **Date: 31/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-05-18

Sample ID No : 2018-05-05-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen	Cross sectional area	Weight of the sample	Failure Load	Compressive strength	Average Compressive Strength
					(mm)	(Sq.mm)	(kg)	(KN)	(N/mm^2)	(N/mm^2)
1	M30 Concrete	M30	03/05/2018	31/05/2018	151.18 X 150.72 X 151.38	22786	8.158	768.0	33.7	33.2
2	M30 Concrete	M30	03/05/2018	31/05/2018	150.89 X 149.19 X 150.64	22512	8.279	723.3	32.1	
3	M30 Concrete	M30	03/05/2018	31/05/2018	149.79 X 150.52 X 149.63	22547	8.183	758.2	33.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

Page 1/1
****End of Report****

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-07-05** **Date: 11/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-05-18
Sample ID No	:	2018-05-07-05 /01
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	04/05/2018	11/05/2018	151.55 X 151.99 X 149.51	23035	8.381	598.1	26.0	25.6
2	M30 Concrete	M30	04/05/2018	11/05/2018	150.09 X 149.20 X 149.77	22395	8.528	585.3	26.1	
3	M30 Concrete	M30	04/05/2018	11/05/2018	150.60 X 149.10 X 151.94	22455	7.965	553.2	24.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-07-05** **Date: 01/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-05-18

Sample ID No : 2018-05-07-05 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	04/05/2018	01/06/2018	151.61 X 150.11 X 150.72	22757	8.346	772.0	33.9	33.2
2	M30 Concrete	M30	04/05/2018	01/06/2018	149.19 X 149.13 X 151.31	22249	8.044	714.0	32.1	
3	M30 Concrete	M30	04/05/2018	01/06/2018	151.52 X 151.86 X 150.24	23011	8.186	770.2	33.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division.
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-08-02** **Date: 12/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-05-18
Sample ID No	:	2018-05-08-02 /01
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	12/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	05/05/2018	12/05/2018	150.63 X 149.49 X 151.04	22517	8.152	579.8	25.8	25.7
2	M30 Concrete	M30	05/05/2018	12/05/2018	151.08 X 151.11 X 151.21	22831	8.137	607.6	26.6	
3	M30 Concrete	M30	05/05/2018	12/05/2018	150.20 X 149.39 X 151.31	22439	8.136	555.8	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-08-02** **Date: 02/06/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Pacakage No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-05-18
Sample ID No	:	2018-05-08-02 /02
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	05/05/2018	02/06/2018	151.76 X 150.54 X 149.71	22845	8.051	770.4	33.7	33.3
2	M30 Concrete	M30	05/05/2018	02/06/2018	149.56 X 151.33 X 149.21	22633	8.139	732.5	32.4	
3	M30 Concrete	M30	05/05/2018	02/06/2018	151.37 X 151.43 X 150.60	22921	8.273	771.7	33.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-16-02** **Date: 21/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-05-18

Sample ID No : 2018-05-16-02 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 21/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	14/05/2018	21/05/2018	151.45 X 149.70 X 151.86	22672	8.308	575.7	25.4	25.8
2	M30 Concrete	M30	14/05/2018	21/05/2018	149.45 X 150.21 X 149.38	22448	7.966	605.5	27.0	
3	M30 Concrete	M30	14/05/2018	21/05/2018	149.43 X 149.42 X 149.89	22327	8.339	557.4	25.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-16-02** **Date: 11/06/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Pacakage No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	15-05-18
Sample ID No	:	2018-05-16-02 /02
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	14/05/2018	11/06/2018	151.43 X 151.50 X 151.77	22942	8.133	761.1	33.2	33.2
2	M30 Concrete	M30	14/05/2018	11/06/2018	151.38 X 151.19 X 151.96	22887	8.480	752.1	32.9	
3	M30 Concrete	M30	14/05/2018	11/06/2018	150.96 X 150.15 X 150.22	22666	8.216	758.3	33.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-17-02** **Date: 22/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-05-18

Sample ID No : 2018-05-17-02 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	15/05/2018	22/05/2018	150.59 X 150.19 X 151.03	22617	7.975	574.3	25.4	25.5
2	M30 Concrete	M30	15/05/2018	22/05/2018	151.57 X 149.85 X 151.90	22713	8.442	597.7	26.3	
3	M30 Concrete	M30	15/05/2018	22/05/2018	150.08 X 150.15 X 151.77	22534	8.216	560.5	24.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-17-02** **Date: 12/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-05-18

Sample ID No : 2018-05-17-02 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	15/05/2018	12/06/2018	149.21 X 150.64 X 150.77	22477	8.504	746.0	33.2	33.0
2	M30 Concrete	M30	15/05/2018	12/06/2018	150.50 X 151.85 X 151.71	22854	8.479	751.1	32.9	
3	M30 Concrete	M30	15/05/2018	12/06/2018	151.53 X 151.59 X 150.65	22970	8.286	758.9	33.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-05-21-02** **Date: 25/05/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore
Address	:	Vidyaranyapura Sub Division, Bangalore
Project Name	:	Package No. 04 (Package consists of 28 works)
Agency	:	M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013
Customer's Reference	:	BBMP/EE/BTP/WO/129/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-18
Sample ID No	:	2018-05-21-02 /01
Customer ID	:	M30 Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	25/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/05/2018	25/05/2018	150.66 X 151.98 X 150.37	22896	8.182	593.2	25.9	25.9
2	M30 Concrete	M30	18/05/2018	25/05/2018	151.16 X 149.97 X 149.85	22671	8.153	611.1	27.0	
3	M30 Concrete	M30	18/05/2018	25/05/2018	149.39 X 151.83 X 150.89	22683	8.202	562.8	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-21-02** **Date: 15/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-18

Sample ID No : 2018-05-21-02 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/05/2018	15/06/2018	151.05 X 150.62 X 151.35	22751	8.256	759.3	33.4	33.3
2	M30 Concrete	M30	18/05/2018	15/06/2018	150.55 X 151.12 X 151.39	22751	8.183	742.3	32.6	
3	M30 Concrete	M30	18/05/2018	15/06/2018	151.89 X 151.15 X 151.79	22958	8.452	778.8	33.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-23-03** **Date: 28/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-05-18

Sample ID No : 2018-05-23-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	21/05/2018	28/05/2018	149.72 X 150.48 X 149.41	22529	8.012	567.5	25.2	25.3
2	M30 Concrete	M30	21/05/2018	28/05/2018	150.92 X 149.99 X 150.80	22637	8.354	603.6	26.7	
3	M30 Concrete	M30	21/05/2018	28/05/2018	149.91 X 149.99 X 151.16	22486	8.218	543.8	24.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Asaistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL PRO Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-23-03** **Date: 18/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-05-18

Sample ID No : 2018-05-23-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	21/05/2018	18/06/2018	151.59 X 150.31 X 151.03	22786	8.148	764.4	33.5	33.2
2	M30 Concrete	M30	21/05/2018	18/06/2018	149.95 X 150.33 X 150.14	22542	8.156	740.3	32.8	
3	M30 Concrete	M30	21/05/2018	18/06/2018	150.35 X 150.38 X 150.00	22609	8.419	752.6	33.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-24-01** **Date: 29/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-05-18

Sample ID No : 2018-05-24-01 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	22/05/2018	29/05/2018	149.69 X 150.57 X 150.49	22538	8.286	570.4	25.3	25.4
2	M30 Concrete	M30	22/05/2018	29/05/2018	149.33 X 150.42 X 151.11	22461	8.448	601.1	26.8	
3	M30 Concrete	M30	22/05/2018	29/05/2018	149.39 X 150.48 X 151.31	22481	8.350	543.6	24.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-24-01** **Date: 19/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-05-18

Sample ID No : 2018-05-24-01 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 19/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	22/05/2018	19/06/2018	149.85 X 149.55 X 149.52	22411	8.375	745.4	33.3	33.0
2	M30 Concrete	M30	22/05/2018	19/06/2018	149.73 X 149.86 X 151.28	22439	8.348	734.9	32.8	
3	M30 Concrete	M30	22/05/2018	19/06/2018	150.38 X 151.48 X 149.06	22780	8.356	752.3	33.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-20-04** **Date: 25/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-04-18

Sample ID No : 2018-04-20-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 25/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/04/2018	25/04/2018	151.96 X 149.12 X 150.51	22660	7.980	567.8	25.1	25.5
2	M30 Concrete	M30	18/04/2018	25/04/2018	149.90 X 151.83 X 151.41	22759	8.237	607.2	26.7	
3	M30 Concrete	M30	18/04/2018	25/04/2018	150.03 X 151.07 X 149.99	22664	8.351	564.4	24.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-20-04** **Date: 16/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-04-18

Sample ID No : 2018-04-20-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	18/04/2018	16/05/2018	149.30 X 149.75 X 149.72	22358	8.161	744.2	33.3	32.9
2	M30 Concrete	M30	18/04/2018	16/05/2018	149.37 X 150.37 X 150.78	22460	8.104	722.4	32.2	
3	M30 Concrete	M30	18/04/2018	16/05/2018	150.38 X 150.33 X 151.11	22606	8.159	753.1	33.3	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-26-05** **Date: 01/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-04-18

Sample ID No : 2018-04-26-05 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	24/04/2018	01/05/2018	150.32 X 149.05 X 151.20	22406	8.406	575.3	25.7	25.9
2	M30 Concrete	M30	24/04/2018	01/05/2018	151.74 X 150.08 X 150.98	22774	8.159	614.2	27.0	
3	M30 Concrete	M30	24/04/2018	01/05/2018	150.36 X 150.15 X 150.91	22576	8.241	563.8	25.0	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-26-05** **Date: 22/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-04-18

Sample ID No : 2018-04-26-05 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	24/04/2018	22/05/2018	150.58 X 149.22 X 150.96	22470	8.133	744.7	33.1	33.1
2	M30 Concrete	M30	24/04/2018	22/05/2018	150.80 X 151.30 X 149.54	22816	8.532	743.8	32.6	
3	M30 Concrete	M30	24/04/2018	22/05/2018	151.47 X 150.33 X 149.25	22772	8.412	762.6	33.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-26-06** **Date: 01/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-04-18

Sample ID No : 2018-04-26-06 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 01/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	24/04/2018	01/05/2018	149.33 X 149.13 X 151.37	22269	8.200	557.1	25.0	25.5
2	M30 Concrete	M30	24/04/2018	01/05/2018	151.80 X 150.83 X 151.79	22895	8.293	611.5	26.7	
3	M30 Concrete	M30	24/04/2018	01/05/2018	150.63 X 150.51 X 149.27	22672	8.032	563.0	24.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-26-06** **Date: 22/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-04-18

Sample ID No : 2018-04-26-06 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 22/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	24/04/2018	22/05/2018	150.00 X 150.96 X 151.71	22645	8.109	763.7	33.7	33.3
2	M30 Concrete	M30	24/04/2018	22/05/2018	149.54 X 150.38 X 149.06	22487	8.257	741.6	33.0	
3	M30 Concrete	M30	24/04/2018	22/05/2018	151.16 X 150.93 X 151.45	22814	8.332	756.2	33.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-30-07** **Date: 05/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-04-18

Sample ID No : 2018-04-30-07 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 05/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	28/04/2018	05/05/2018	151.75 X 150.79 X 150.94	22882	8.554	588.7	25.7	25.5
2	M30 Concrete	M30	28/04/2018	05/05/2018	151.22 X 149.02 X 150.42	22535	8.388	599.3	26.6	
3	M30 Concrete	M30	28/04/2018	05/05/2018	150.24 X 151.23 X 151.37	22720	8.157	549.5	24.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-30-07** **Date: 26/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-04-18

Sample ID No : 2018-04-30-07 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	28/04/2018	26/05/2018	149.79 X 151.82 X 149.94	22741	8.111	754.2	33.2	33.0
2	M30 Concrete	M30	28/04/2018	26/05/2018	149.71 X 149.27 X 149.09	22347	8.158	722.3	32.3	
3	M30 Concrete	M30	28/04/2018	26/05/2018	149.87 X 150.20 X 149.18	22510	8.221	757.5	33.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-04-03** **Date: 09/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 04-05-18

Sample ID No : 2018-05-04-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	02/05/2018	09/05/2018	149.25 X 149.84 X 151.11	22364	8.124	563.8	25.2	25.4
2	M30 Concrete	M30	02/05/2018	09/05/2018	151.09 X 151.37 X 151.32	22870	8.470	601.8	26.3	
3	M30 Concrete	M30	02/05/2018	09/05/2018	149.80 X 151.19 X 151.44	22649	8.494	559.4	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-04-03** **Date: 30/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 04-05-18

Sample ID No : 2018-05-04-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 30/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	02/05/2018	30/05/2018	149.54 X 149.17 X 150.23	22307	8.504	746.6	33.5	33.3
2	M30 Concrete	M30	02/05/2018	30/05/2018	149.65 X 151.75 X 151.13	22708	8.220	746.2	32.9	
3	M30 Concrete	M30	02/05/2018	30/05/2018	150.93 X 150.91 X 150.80	22776	8.249	765.6	33.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

Page 1/1
****End of Report****

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-04-04** **Date: 09/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 04-05-18

Sample ID No : 2018-05-04-04 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	02/05/2018	09/05/2018	150.98 X 149.04 X 150.90	22502	8.268	584.2	26.0	25.9
2	M30 Concrete	M30	02/05/2018	09/05/2018	150.87 X 149.18 X 149.77	22507	8.151	601.9	26.7	
3	M30 Concrete	M30	02/05/2018	09/05/2018	150.45 X 150.06 X 151.40	22576	8.243	562.1	24.9	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-04-04** **Date: 30/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 04-05-18

Sample ID No : 2018-05-04-04 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 30/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	02/05/2018	30/05/2018	151.63 X 150.31 X 151.40	22791	8.402	757.7	33.2	33.1
2	M30 Concrete	M30	02/05/2018	30/05/2018	150.84 X 151.58 X 151.64	22864	8.405	749.3	32.8	
3	M30 Concrete	M30	02/05/2018	30/05/2018	151.75 X 151.66 X 151.07	23014	8.451	763.0	33.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

****End of Report****

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924626 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-14-03** **Date: 18/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-05-18

Sample ID No : 2018-05-14-03 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	11/05/2018	18/05/2018	150.28 X 151.56 X 149.70	22776	8.244	572.7	25.1	25.4
2	M30 Concrete	M30	11/05/2018	18/05/2018	149.69 X 151.17 X 151.99	22628	8.042	594.6	26.3	
3	M30 Concrete	M30	11/05/2018	18/05/2018	150.78 X 150.47 X 149.66	22687	8.435	561.2	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-05-14-03** **Date: 08/06/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 14-05-18

Sample ID No : 2018-05-14-03 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/06/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	11/05/2018	08/06/2018	149.98 X 149.77 X 150.15	22463	8.313	750.8	33.4	33.1
2	M30 Concrete	M30	11/05/2018	08/06/2018	149.41 X 151.31 X 150.37	22607	8.499	723.6	32.0	
3	M30 Concrete	M30	11/05/2018	08/06/2018	151.76 X 151.61 X 151.52	23008	8.433	776.5	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-19-12** **Date: 24/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-12 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	17/04/2018	24/04/2018	150.41 X 150.74 X 151.00	22673	8.234	568.0	25.1	25.5
2	M30 Concrete	M30	17/04/2018	24/04/2018	149.91 X 151.95 X 149.18	22779	8.055	610.1	26.8	
3	M30 Concrete	M30	17/04/2018	24/04/2018	150.41 X 149.87 X 150.97	22541	8.271	557.1	24.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-19-12** **Date: 15/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 19-04-18

Sample ID No : 2018-04-19-12 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	17/04/2018	15/05/2018	149.58 X 150.76 X 150.67	22551	8.245	765.5	33.9	33.3
2	M30 Concrete	M30	17/04/2018	15/05/2018	150.41 X 150.99 X 151.90	22710	8.400	739.2	32.5	
3	M30 Concrete	M30	17/04/2018	15/05/2018	149.65 X 149.88 X 149.63	22429	8.237	751.4	33.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2018-04-23-07 **Date: 27/04/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Package No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore- 560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-04-18

Sample ID No : 2018-04-23-07 /01

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 27/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	20/04/2018	27/04/2018	149.34 X 150.88 X 150.94	22532	8.112	580.8	25.8	25.3
2	M30 Concrete	M30	20/04/2018	27/04/2018	151.40 X 151.52 X 149.32	22939	8.328	598.9	26.1	
3	M30 Concrete	M30	20/04/2018	27/04/2018	151.38 X 149.53 X 150.19	22637	8.382	545.3	24.1	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Divisior
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-04-23-07** **Date: 18/05/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, Bangalore

Address : Vidyaranyapura Sub Division, Bangalore

Project Name : Pacakage No. 04 (Package consists of 28 works)

Agency : M/s. Ram and company, Sri. C R GIRISH, No. 12, Patel Pillegowda layout, Ramachandrapura, Bangalore-560013

Customer's Reference : BBMP/EE/BTP/WO/129/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-04-18

Sample ID No : 2018-04-23-07 /02

Customer ID : M30 Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/05/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	M30 Concrete	M30	20/04/2018	18/05/2018	151.63 X 150.37 X 151.95	22801	8.231	753.5	33.0	33.2
2	M30 Concrete	M30	20/04/2018	18/05/2018	151.84 X 149.10 X 150.75	22640	8.216	739.8	32.7	
3	M30 Concrete	M30	20/04/2018	18/05/2018	150.78 X 151.55 X 151.61	22851	8.397	771.3	33.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig. Date. BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com